

EXHIBIT 1

Compounds with negligible reactivity with OH RADICAL

Non-Photochemically reactive compound #6

Zero-volatile organic compounds - Brominated Family

1-Bromopropane (pure) - Solubility profile in  
Solvent Solubility Resins (10 grams)

100 GRAMS/solvent	S	Styrene-Butadiene	Isobutene
"	S	Styrene	"
"	S	Styrene-Isoprene-Butadiene	"
"	PS	Nitrocellulose	Coating resin
"	S	Alkyd Resin	"
"	PS	Silicone	"
"	PS	Cellulose Acetate Butyrate	"
"	S	Acrylic	"
"	S	Terpene	Tackifier
"	S	Polychloroprene	Elastomeric
"	S	Resin ester	Tackifier
"	S	Coumarone-Indene	"
"	C	PVC	Elastomer
"	PS	Epoxy	Resin
"	S	Chlorinated Polyurethane	"
"	PS	Phenolic	"
"	S	Olefin	"
"	S	Vinyl	"

S = Soluble

PS = Partially soluble

C = Cloudy solution

These combinations can be used in adhesive, ink or coating formulations.

PB